

3-STRAND NYLON ROPE INFORMATION

mm Dia	Wt per 220 mtrs	MBL tonne
6	5	0.809
8	8	1.408
10	14	2.162
12	20	3.070
14	26	4.080
16	35	5.294
18	44	6.559
20	54	8.078
22	65	9.588
24	78	11.424
28	91	15.198
32	122	19.584
36	176	24.480
40	217	29.988

MBL for indication purposes only – not test certificated

High Elasticity – Caution large amount of energy stored within the rope

Manufactured in Portugal

EN ISO 1440:2004

Density: 1.14

Melt Point: 248°C