

3-STRAND POLYESTER ROPE INFORMATION

mm Dia		Kg per 100 mtrs		MBL tonne
8		4.9		1.07
10		7.6		1.65
12		10.9		2.34
14		14.9		3.15
16		19.4		4.06
18		24.6		5.09
20		30.3		6.22
22		36.7		7.45
24		43.7		8.78
26		51.2		10.30
36		98.2		19.16

MBL for indication purposes only – not test certificated

High Tenacity Polyester

Manufactured in Europe

EN ISO 1141

Density: 1.38

Melt Point: 260°C

Colours: White, Black, Navy Blue

