

### 3-STRAND ORANGE POLYETHYLENE ROPE INFORMATION

mm Dia	Wt per 220 mtrs	MBL tonne
6	4	0.418
8	7	0.725
10	11	1.112
12	16	1.581
14	21	2.132
16	28	2.754
18	35	3.448
20	44	4.273
22	53	5.080
24	63	5.996
28	86	8.078
32	113	10.404
36	143	13.056
40	176	14.014

MBL for indication purposes only – not test certificated

Manufactured in Portugal

EN ISO 1969:2004

Density: 0.95

Melt Point: 140°C

