

### 3-STRAND BLUE POLYPROPYLENE ROPE INFORMATION

mm Dia	Wt per 220 mtrs	MBL tonne
6	4	0.604
8	6	1.030
10	10	1.571
12	14	2.203
14	19	2.948
16	25	3.774
18	32	4.712
20	39	5.722
22	48	6.844
24	57	8.038
28	77	10.710
32	102	13.668
36	129	17.034
40	159	20.808

MBL for indication purposes only – not test certificated

Manufactured in Portugal

EN ISO 1346:2004

Density: 0.91

Melt Point: 165°C

