

### 3-STRAND WHITE STAPLESPUN POLYPROPYLENE ROPE INFORMATION

mm Dia	Wt per 220 mtrs	MBL tonne
6	4	0.612
8	6	1.030
10	10	1.571
12	14	2.203
14	20	2.948
16	26	3.825
18	32	4.712
20	40	5.722
22	48	6.844
24	57	8.160
28	78	10.812
32	102	13.668
36	129	17.340
40	159	20.808

MBL for indication purposes only – not test certificated

Manufactured in Portugal

EN ISO 1346:2004

Density: 0.91

Melt Point: 165°C

