

### 3-STRAND SYNTHETIC HEMP ROPE INFORMATION

mm Dia	Wt per 220 mtrs	MBL tonne *
6	4	0.356
8	6	0.611
10	10	0.917
12	14	1.366
14	18	1.774
16	22	2.222
18	28	2.783
20	35	3.487
22	42	4.180
24	51	4.925
28	68	6.628
32	88	8.463
36	112	10.605
40	138	13.154

MBL for indication purposes only – not test certificated

\* Spliced break Load

3.2% Elongation at 10% of Breaking Load

Manufactured in Germany

Density: 0.91

Melt Point: 165°C

