

### 3-STRAND SYNTHETIC HEMP ROPE INFORMATION

mm Dia	Wt per 220 mtrs	MBL tonne *	SWL @ 20% in Kg
6	4	0.360	72
8	6	0.600	120
10	10	0.900	180
12	14	1.340	268
14	18	1.740	348
16	22	2.180	436
18	28	2.730	546
20	35	3.420	684
24	51	4.830	966
28	68	6.470	1294
32	88	8.300	1660
36	112	10.400	2080
48	166 (100m)	16.000	3200

MBL for indication purposes only – not test certificated

\* Spliced break Load

3.2% Elongation at 10% of Breaking Load

Manufactured in Germany

Density: 0.91

Melt Point: 165°C

